


Visible Nitrile Gloves



PRODUCT INFORMATION	
MATERIAL	Nitrile
COLOR	Green, orange and black
TYPE	Ambidextrous, non-sterile, single-use
INTERIOR	Powder-free
EXTERIOR	Fully textured
SIZES	S - 2XL
COUNTRY OF ORIGIN	Thailand
STORAGE	Store in original packaging in a cool, dry and well ventilated area, away from dust, direct sunlight, moisture, x-ray and excessive heat above 100°F (37°C)



PHYSICAL PROPERTIES		
AQL	1.5	
GLOVE WEIGHT	5.8g (medium)	
GLOVE THICKNESS	6mil, 0.15mm	
GLOVE LENGTH	9"	
	BEFORE AGING	AFTER AGING
TENSILE STRENGTH (MPA)	22 min	22 min
ULTIMATE ELONGATION	500%	400%



QUALITY STANDARDS	
FDA STATUS	(21 CFR 177) compliant for food handling
AUDIT STANDARDS	Manufactured in an ISO 9001:2015 and an ISO 13485:2016 facility
TEST STANDARDS	EN ISO 374-1:2016/Type B EN ISO 374-5:2016 Resistance to Bacteria, Fungi & Virus

PACKAGING & ORDERING INFORMATION							
ORANGE CODE	GREEN CODE	BLACK CODE	SIZE	PURCHASE UNIT	CASE DIMENSIONS (LxWxH)	CASE WEIGHT	CUBIC FEET
1030202	1031202	1032202	S	1 case of 1,000 Gloves (100/box x 10)	15.8" x 9.8" x 9.7"	12.6lbs	0.62ft ³
1030302	1031302	1032302	M				
1030402	1031402	1032402	L				
1030502	1031502	1032502	XL				
1030602	1031602	1032602	2XL	1 case of 900 Gloves (90/box x 10)			

RESISTANCE OF GLOVES TO PERMEATION BY CHEMICALS

CHEMICAL	EN ISO 374-1:2016 PERFORMANCE LEVEL	EN 374-4:2019 MEAN DEGRADATION / %				
Sodium Hydroxide 40% (K)	6	1.3				
Ammonium Hydroxide 25% (O)	1	7.8				
Sulphuric Acid 96% (L)	1	Fully disintegrated				
Hydrogen Peroxide 30% (P)	6	17.3				
Formaldehyde 37% (T)	6	16.0				
EN ISO 374-1:2016 - permeation levels are based on breakthrough times as follows:						
Performance Level:	1	2	3	4	5	6
Minimum breakthrough time (Min):	>10	>30	>60	>120	>240	>480
Safety gloves to protect against chemicals are classified according to their permeation time (time taken for the chemical to penetrate the glove) and number of chemicals tested:						
<ul style="list-style-type: none"> • Type A - at least 30min each for at least 6 test chemicals • Type B - at least 30min each for at least 3 test chemicals • Type C - at least 10min each for at least 1 test chemicals 						
EN 374-4:2019 - Degradation results indicate the change in puncture resistance of the gloves after exposure to the challenge chemical						
EN ISO 374-5:2016 - Resistance to Bacteria and Fungi = Pass, Resistance to Virus = Pass						

MANDATORY STATEMENTS EN ISO 374-1:2016

"This information does not reflect the actual duration of protection in the workplace and the differentiation between mixtures and pure chemicals."
 "The chemical resistance has been assessed under laboratory conditions from samples taken from the palm only (except in cases where the glove is equal to or over 400mm - where the cuff is tested also) and relates only to the chemical tested. It can be different if the chemical is used in a mixture."
 "It is recommended to check that the gloves are suitable for the intended use because the conditions at the workplace may differ from the type depending on temperature, abrasion and degradation."
 "When used, protective gloves may provide less resistance to the dangerous chemical due to changes in physical properties. Movements, snagging, rubbing, degradation caused by the chemical contact etc. may reduce the actual use time significantly. For corrosive chemicals, degradation can be the most important factor to consider in selection of chemical resistant gloves."
 "*The penetration resistance has been assessed under laboratory conditions and relates to the tested specimen.*"



Contact us today to receive samples or for more information on this product.

Eagle Protect PBC
 sales@eagleprotect.com
 eagleprotect.com
 1 800 384 3905

Head Office
 3079 Harrison Avenue #21
 South Lake Tahoe
 California 96150



SAFEGUARD WHAT MATTERS™